

ORCON MULTIBOND

Rolls of joint adhesive for interior and exterior use



Technical data

Substance		
Material	SOLID acrylate, no plasticisers, solvents, emulgators or preservatives	
Release film	Silicone-coated PP film	
Attribute	Regulation	Value
Colour		translucent green
Width of adhesive bead		11 mm
Thickness of adhesive bead		3 mm
Moisture resistance		waterproof
Bonding requirement, non-aged/ aged	DIN 4108-11	passed
Adhesion	BS EN 1939	16 N/cm
Application temperature	from -15 °C ; 5 °F	
Temperature resistance	permanent -40 °C to 100 °C ; -40 °F to 212 °F	
Storage	horizontal, cool and dry, protect from direct sunlight	

Area of application

Solvent-free, permanent, elastic, frost-resistant airtight adhesive that can be applied straight from a roll for bonding all types of vapour retarders and vapour barriers – e.g. pro clima INTELLO, DB+, INTESANA, DASATOP and DA, as well as PE, PA, PP or aluminium sheeting – on mineral or rough adjacent components such as masonry, plasterwork, concrete or roughly sawn wood.

Sticking of windtight joints on commercially available underlay and sarking membranes (e.g. those made of PE and PET). Joint adhesion in combination with the pro clima SOLITEX MENTO family of products and SOLITEX UM fulfils the requirements of the ZVDH product data sheets.

Windtight sticking of wall-lining membranes of all types (e.g. pro clima SOLITEX FRONTA family).

Forms of delivery

Art. no.	GTIN	Length	Width	Weight	Sales unit	Container
1AR00501	4026639205018	10 m	11 mm	3.7 kg	1	105
1AR00572	4026639205728	20 m	11 mm	0.815 kg	6	630

Advantages

- ✓ Subsequent work can be started quickly: joint adhesive from a roll, no drying time - joint can be subjected to loading immediately
- ✓ Can be used flexibly: sticks in a permanent, reliable manner thanks to waterproof SOLID adhesive
- ✓ Reliable even during frosty conditions: sticks reliably above -15 °C
- ✓ Construction in adherence with standards: for airtight bonding in accordance with DIN 4108-7, SIA 180 and RT 2012
- ✓ Excellent values in the hazardous substance test, has been tested according to the ISO 16000 evaluation scheme

Substrates

Clean substrates before sticking. Mineral surfaces (plaster or concrete) may be slightly moist.

Adhesion to frozen surfaces is not possible. The substrate material must be free of water-repellent substances (e.g. grease or silicone). Subsurfaces must be stable - if necessary, a mechanical support (pressure lath) must be used (e.g. on crumbling substrates).

Permanent adhesion is achieved on all pro clima interior and exterior membranes, other vapour retarder and airtight membranes (e.g. those made of PE, PA, PP and aluminium) as well as other underlay/sarking and wall lining membranes (e.g. those made of PP and PET).

Bonds can be created on mineral substrates (e.g. plaster or concrete), roughly sawn, planed and painted wood, hard plastics and rustproof metal (e.g. pipes, windows etc.) and hard wood-based panels (chipboard, OSB, plywood, MDF panels).

The best results in terms of structural stability are achieved on high-quality substrates.

It is your responsibility to check the suitability of the substrate; adhesion tests are recommended in certain cases.

Pretreatment with TESCON PRIMER is recommended in the case of substrates with insufficient stability.

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Ecological Building Systems

For stockist information and full technical support for your project, please contact Ecological Building Systems or visit www.EcologicalBuildingSystems.com




Ireland: 046 9432104 Fax: 046 9432435 UK: 01228 711 511 Fax: 01228 712 280

info@EcologicalBuildingSystems.com

General conditions

The bonds must not be subjected to tensile forces. It may be advisable to use mechanical reinforcements.
Rub the bond firmly into place (e.g. using the pro clima PRESSFIX application tool).
The product achieves its final level of strength after approx. 24 h.



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions)



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Ecological Building Systems

For stockist information and full technical support for your project, please contact Ecological Building Systems or visit www.EcologicalBuildingSystems.com



Ireland: 046 9432104 Fax: 046 9432435 UK: 01228 711 511 Fax: 01228 712 280

info@EcologicalBuildingSystems.com